

Review Paper

The Role of Novel Nanomaterials in Biomedical Applications

Samavia Siddique^{1*} and Hifza Jamil¹

¹ Department of Biotechnology, University of Veterinary and Animal Sciences (UVAS), Outfall Rd, Data Gunj Buksh Town, Lahore 54000, Pakistan.

Correspondence: samavia.4012@gmail.com

Abstract:

Nanotechnology is an innovative field of science that has revolutionized numerous biomedical applications due to their unique physicochemical and biological properties. This field deals with small sized materials called nanomaterials, which can be metals, polymers, or semiconductors, having different properties that scientists use according to their requirements. They possess properties like high surface area, biocompatibility, and antioxidant capability and are also antimicrobial. These properties have enhanced their ability to diagnose the disease early, especially helping drug delivery to precise targets where they can release drugs only when specifically stimulated. Nanomaterials have improved the precision and efficacy of cancer treatments, imaging techniques, and regenerative medicine. Biosensors and biocatalysts utilizing nanomaterials have significantly enhanced the sensitivity and efficiency of diagnostics and industrial applications. Despite these advancements, challenges like toxicity, accumulation in biological systems, and environmental impacts still exist that raise concerns regarding biocompatibility and safety and need to be catered prior to large scale applications and marketing.

Keywords: Nanotechnology, Theranostics, Nanomaterials, Biosensors, Biocompatibility

Citation: Siddique S., Jamil H. (2025). The Role of Novel Nanomaterials in Biomedical Applications. *J Life Sci Inform*, 1(1), 1-24.

Copyright: © The Authors

Licensing: This article is open access and is distributed under the terms of Creative Commons Attribution 4.0 International License.

Conflict of Interest: Author(s) declared no conflict of interest

Introduction:

Nanotechnology has endured exponential growth in the last decade and has offered several benefits. Employing nano-scaled particles ranging between 1 and 100nm in one dimension has revolutionized almost every walk of life (Najahi-Missaoui, Arnold, & Cummings, 2020). Particularly, nanoparticles have attained special attention in biomedical field because of their specific characteristics like antimicrobial activity (Mahmoudi Khatir & Khorsand Zak, 2024), antioxidant properties, catalytic activity (Etefa, Nemera, Etefa, & Kumar, 2024), loading capacity (Ta et al., 2024), anti-inflammatory properties (Deena Dayal et al., 2024), and many other. Nanotechnology covers a wide range of application from diagnostics to imaging, therapeutics, regenerative medicines and personalized medicines. Nanoparticles have played a key role in all these applications because of their size, biocompatibility, and large surface area (Esmaeili et al., 2022). They are able to carry the drug to the specific target points thus making targeted drug delivery possible. In addition, they can they are also effective in transporting the protein, DNA, and hydrophobic drug molecules which are difficult to deliver with conventional tools and solvents (Figure 1) (Iqbal et al., 2024). Interestingly, more than ninety nano-drugs are available in the market (Jia et al., 2023) and many in progress.

Although nanotechnology offers a lot of improvement in biomedical field, there are still some concerns. The main factor that needs to be consider is accumulation of nanoparticles in living organisms because of their size and ability to cross the biological barrier (H. Wu et al., 2024). Research should be conducted to make biodegradable nanoparticles through green synthesis so that nanoparticles could not get accumulated and cause further problems. Many efforts are going on to overcome this issue. For example, green synthesis of metal nanoparticles using plant growth promoting rhizobacteria that offers eco-friendly and sustainable approach is under research (Saberi Riseh & Gholizadeh Vazvani, 2024). The other major concerns related to nanoparticles are their cytotoxicity and their impact on the natural ecosystem because of their size. To overcome this problem regulations and policies are made by different organizations at national and international level (Tran et al., 2024).

The present review explores the history, classification, production methods, future perspective, challenges and the applications of nanoparticles in the biomedical field. It emphasize the role of nanoparticles in different biomedical techniques and approaches like drug delivery, diagnostics and imaging. It provides an understanding of the importance of nanoparticles in tissue engineering and regenerative medicine and how they can help in the treatment and diagnosis of different diseases. But their limitations like cytotoxicity, accumulation and manufacturing of these nanoparticles from laboratory to large scale up industry is still associated with difference of opinions, though researchers are going on to overcome these challenges and to exploit their full potential.




Fig. 1: Overview of Nano-materials in Biomedicine (This diagram has been prepared by BioRender <https://BioRender.com>)

3. History of Nanomaterials in Biomedicine

Brief history of nanomaterials in biomedical research

One of the earliest examples of nanotechnology is the Lycurgus cup produced in 4th century by Romans. It was renowned due to its dichroic nature (appears green in regular light or red or purple when light shines through it). It possessed this ability because the materials used to construct it were gold or silver nanoparticles (Freestone, Meeks, Sax, & Higgitt, 2007). Nevertheless, the proper scientific study of nanoparticles began in 1857, when Michael Faraday highlighted his work at the Royal Society of London that nanoscale material behave differently than those at larger level. For example gold looks yellow in bulky form, as opposed to its nanoscale counterpart exhibit wide range of colors including red or purple colour depending upon on their size, shape, and surface plasmon resonance properties (Faraday, 1857). Moving forward, in 1959, Richard Feynman's statement caught attention of the research community, stating "There is Plenty of Room at the Bottom" during his lecture at the American Physical Society meeting. He even mentioned the use of tiny robots in medicine to examine, treat, or support damaged organs (Feynman, 2018). Interestingly, in 1981, Gerd Binning and Heinrich Rohrer developed the Scanning Tunneling Microscope (STM) by which scientist were able to scan the individual atom, and in 1986 the more advanced version of STM, the Atomic Force Microscope (AFM) was invented by Calvin Quate and Christoph Gerber, which further enhanced the ability to observe and manipulate the nanoscale structures at atomic levels (Kateb & Heiss,

2013). These inventions led to the progress of nanotechnology in many disciplines including biomedicine.

In 1991, Drexler, Peterson and Pergamit published a book "Unbounding the Future: the Nanotechnology Revolution" in which the term "nano medicine" was presumably used for the first time (Bayda, Adeel, Tuccinardi, Cordani, & Rizzolio, 2019). Similarly, in the early 20th century, the concept of magic bullets was introduced by Paul Ehrlich's for targeted drug delivery inspired by the concept of "Freikugeln" in the opera Der Freischutz, resulting in the creation of nanoparticles in medicine. In the late 1960s, the first nanoparticle was created by Professor Speiser's team for assisting in therapeutics (Kreuter, 2007). It was experimentally proven that insulin nano capsules showed long term results, both subcutaneously ($P<0.001$) and through intragastrical routes ($P<0.001$) on glycemia as compared to regular insulin (Damgé, Michel, Aprahamian, & Couvreur, 1988).

Milestones in nanomaterial applications for healthcare and treatment

Another breakthrough was reported at the beginning of 2005 the first economical drug product using nanoparticles (AbraxaneTM, a composition of human serum albumin nanoparticles with paclitaxel) introduced on the market by US company, Abraxis Oncology (Kreuter, 2007). In 1995 doxil became the first FDA approved drug and sales in USA and Europe in 1996 (Barenholz, 2012). There are a number of other nano drugs which were approved by FDA after that, for example DaunoXome[®] approved in 1996, Visudyne[®] approved in 2000, NanoTherm[®] approves in 2003, DepoDur[®] approved in 2004, Cimzia[®] approved in 2008, FerahemeTM (Ferumoxytol) approved in 2009, Marqibo[®] and Opaxio[®] approved in 2012, and Kadcyla[®] approved in 2013 (Weissig, Pettinger, & Murdock, 2014). All these achievements proved very beneficial especially in the field of biomedicine.

4. Classification and production of nanoparticles

Nanomaterial classification is crucial for understanding their diverse properties, maximizing their applications, and determining their regulatory and potential interactions with biological systems. Nanomaterials have diversity in their structures, compositions, and functionalities, that's why they are categorized using various criteria. This classification is based on the material they are made of, along with their properties in order to identify the most suitable nanomaterials for specific biomedical applications.

4.1 Types of Nanomaterials

Nanomaterials are being classified based on their composition, having specific properties. The primary classifications include metallic nanomaterials, polymeric nanomaterials, carbon-based nanomaterials, hybrid nanomaterials, and supramolecular nanomaterials (Figure 2). These categories are distinguished by their unique physiochemical properties making them suitable for different biomedical applications. These include several categories, that have been discussed in the next section.

4.1.1 Metallic nanomaterial

Metallic nanomaterials are known for their biocompatibility, thermal conductivity, and have potential multifunctional applications. The most commonly used nanomaterials include gold, silver, and iron oxide nanomaterials. Gold nanomaterials exhibit a strong surface plasmon resonance (SPR) that have applications for the treatment of cancer, theranostics, photothermal therapy (PTT), biosensing, and imaging. (Kolodin, Syrovashin, & Korotaev, 2024). Silver nanoparticles have antimicrobial properties making them beneficial against bacteria, algae, and fungi. (El-Sheekh, Alwaleed, Kassem, & Saber, 2020; Mohamedsalih & Sabir, 2020) (Encabo-Berzosa et al., 2017). Iron oxide nanomaterials have superparamagnetic properties, making them efficient in targeted drug delivery.(Nasrollahi & Alizadeh, 2024) Recently nanomaterials are being made by combining two metals, such as gold-silver or gold-platinum, having increased catalytic activity and stability that can be used for Multi-Modal Therapies and Imaging.

4.1.2 Polymeric nanoparticles

Polymeric Nanomaterial are constructed from polymers like polyethylene glycol (PEG) or polylactide-co-glycolide (PLGA), have applications in the in vitro transfer of therapeutic and diagnostic agents because of their bio-resorbability, tunable properties, and ability to encapsulate diverse therapeutic agents. While non-biodegradable polymers such as PolyMethyl MethAcrylate (PMMA) have been explored, their non-biocompatibility poses significant limitations, making them less favorable for biomedical applications. (Kluin, Van der Mei, Busscher, & Neut, 2013), which necessitates the need for biodegradable nanoparticle production. They are made from polylactic acid (PLA), polyglycolic acid (PGA), poly(lactic-co-glycolic acid) (PLGA), and polycaprolactone (PCL), all of these degrades into a-toxic byproducts (Van et al., 2024).They are used for targeted nano-delivery of cancer therapeutics (Anees et al., 2023), as effective gene-transfer material (Yang et al., 2024) and in vaccination protocols to enhance the delivery and efficacy (Hardenberg et al., 2024). Dendrimers are synthesized using organic polymers and are well-defined, monodispersed, and have multiple functional groups that allow surface modification. They also have many biomedical applications including targeted drug delivery. (Palombarini et al., 2021).

4.1.3 Carbon-based nanomaterials

Carbon-based nanomaterials are diverse in nature because carbon possesses various allotropes. They have many applications because of their physiochemical properties, such as high mechanical strength, surface area electric conductivity, and biocompatibility. These include fullerenes, graphene, quantum dots, graphene oxide, carbon nanofiber, and carbon nanotubes. Fullerenes are spherical molecules composed of carbon, C_{60} can intermediate photosensitized reaction as they absorb a broad spectrum of light this ability makes them beneficial in photodynamic cancer therapy. (Lee et al., 2021). Carbon quantum dots (CQDs) are spherical and smaller than 9nm in diameter. They have absorbance, photoluminescence, and photoinduced electron transfer properties making them advantageous in bioimaging and therapeutics. (Jain,

Sahu, Bhatia, & Yadav, 2024). Carbon-based nanomaterials because of their versatility in structure and properties have numerous biomedical applications.

4.1.4 Hybrid Nanomaterials

Hybrid nanomaterials are made from two distinct types of material on a nanoscale level in order to enhance properties of both. This category includes organic-inorganic hybrids, Polymer-Metal hybrids, Carbon-Based hybrids and interestingly due to their synergistic properties. All of these have vast applications in biomedical science.

4.1.5 Supramolecular Nanomaterial

Supramolecular means more complex than a molecule. Supramolecular-based nanomaterials (SMBNs) are made by self-assembling molecules that do not have covalent interactions. SMDNs rely on dynamic and reversible interactions, causing them to have highly organized, self-assembling structures such as micelles, nanotubes (Saji, 2022), nanospheres, nanocapsules, and hydrogels (Wang et al., 2024). They are further classified based on the building blocks like peptide amphiphiles, cyclodextrins, amyloid protein, and supramolecular polymers. Their functionality at the nanoscale level; makes them significant in the biomedical field.

4.2 Production Methods

For the production of nanomaterials, it is important to understand that their synthesis involves techniques designed to control their size, shape, and surface properties at the nanoscale. Various methods are employed to tailor nanomaterials for specific applications, particularly in the biomedical field (Figure 2).

Top-down approaches are commonly used, which involve breaking down bulk materials into nanoscale particles through physical or mechanical methods. The method includes mechanical milling, lithography, particle beam lithography (Shahali et al., 2019), photolithography, and Laser ablation to produce nanoscale structures.

When bulk structures are broken then Bottom-up approaches are used which are more precise and specified. The bottom-up approach involves the building up of particles on the nanoscale by using atoms and molecules as a building unit. Chemical Vapor Deposition (CVD) is a method in which thin film is obtained by a chemical reaction of gaseous precursors. (Hoyos-Palacio et al., 2019). Spray pyrolysis is a method in which solution is atomized in fine droplets and is rapidly heated to evaporate solvent and left outs are nanoparticles (Hoyos-Palacio et al., 2019). Sol-Gel Process involves the conversion of polymers into fine gels of the polymer into fine gels and then drying or calcination to yield nanoparticles (Usha, Prasad, & Ramesh, 2023).

Biological systems are also being utilized, such as microbes (John et al., 2020), plant extracts, or enzymes, to produce nanoparticles in an eco-friendly manner through bottom-up approach. Moreover, Bottom-up approaches are widely adopted for their ability to produce nanoparticles with high precision and scalability.




Fig. 2: Classification and Synthesis Methods of Nanomaterials (This diagram has been prepared by BioRender <https://BioRender.com>)

5. Emerging Nanomaterials in Biomedical Research

Nanomaterials have revolutionized biomedical research due to their properties, biocompatibility, and efficiency. Some newly emerging nanomaterials include silicon Nanoparticles (SiNPs) and sustainable and biodegradable nanomaterials. We have explained them briefly in the following sections:

5.1 Silicon Nanoparticles (SiNPs)

Silicon is the most abundant electropositive element in the Earth's crust. It is biocompatible and bio-durable, having properties like hydrophobicity, chemical stability, thermal stability, and low surface tension. Particularly, Gadolinium silicate-coated porous silicon nanoparticles are used as tumor-targeting agent (Baati et al., 2023), Gadolinium silicate-coated porous silicon nanoparticles

are used as an MRI contrast agent and drug delivery carrier (Jin et al., 2022) , and as biosensors (Q. Zhao et al., 2022).

5.2 Sustainable and Biodegradable Nanomaterials

As environmental concerns grow, sustainable and biodegradable nanomaterials have emerged as vital alternatives to conventional materials. These nanomaterials, including cellulose nanocrystals, chitosan, and PolyLactic Acid (PLA), are derived from renewable resources and designed to degrade into non-toxic byproducts. In drug delivery, biodegradable nanomaterials enable sustained drug release, reducing the need for repeated dosing and invasive retrieval after treatment. In regenerative medicine, these materials act as scaffolds for tissue repair, gradually degrading as new tissue forms [23]. These sustainable materials also hold potential in bioimaging [24] and diagnostics, where biodegradable agents offer lower toxicity and better clearance from the body. Their alignment with green chemistry principles ensures they meet both biomedical needs and environmental sustainability goals.

6.Key Biomedical Applications of Nanomaterials

Nanotechnology has transformed the biomedical field by introducing the innovative ways in the early diagnosis and treatment of diseases (Figure 3). Here is the crux of some vital biomedical applications of nanotechnology:

6.1 Drug Delivery System

Most therapeutics and treatment options involve non-targeted drug delivery systems that cause several side effects. In the case of cancer, chemotherapy is one of the most used treatment options but because of its non-targeted nature, it causes some detrimental side effects in the patients. They may face problems like constipation, vomiting, diarrhea, and thrombocytopenia due to toxicity of chemotherapeutic drugs (Kundu et al., 2020).

To solve this problem nanotechnology has played a key role by lowering the side effects and selectively targeting the cancer cells. Literature shows that Mg⁺ doped ZnO nanoparticles have been used for the optimization of drug delivery especially in case of gastric cancer (Ouyang et al., 2024). Research shows that Carbon-based nano-materials drug delivery systems are capable of targeted treatment of solid tumors (Albuquerque et al., 2021). Likewise, gold nanoparticles are used as drug carriers in the treatment of rheumatoid arthritis and increased the therapeutic efficiency of the drug (Fan, Li, Jin, & Li, 2024).

6.2 Diagnostics and imaging

Early diagnosis of disease is the most important step for the recovery from that particular disease. In case of cancer the main reason of death is the late diagnosis (Darré et al., 2023). This may be because we still do not have advanced diagnosis protocols. One of the main techniques that is used is magnetic resonance imaging which has high resolution but less specificity and the other

diagnostic assay is Polymerase Chain Reaction (PCR) that provide specificity but is time taking (Farinha, Coelho, Reis, & Gaspar, 2021).

In this hour of need, magnetic and fluorescent nanoparticles provide a potential solution to this problem using optical fluorescence imaging using gold nanoparticles (AuNPs). With their biocompatibility, high surface area, fluorescence and their ability to bind to biological element they are widely used in optical fluorescence imaging (Esmaeili et al., 2022). For instance, 5-HT-Fe3O4-Cy7 nanoparticles (5HFeC NPs) are used in imaging for accurate detection of Atherosclerotic plaque. This is done by targeting active myeloperoxidase using fluorescence imaging (Tong et al., 2021). For fast fluorescence imaging and antibacterial treatment of bacterial keratitis novel NTR-responsive copper-based nanoparticles (Cu2-xSe@BSA@NTRP) were designed, which shows significant efficacy (95%) and significant re-epithelialization against *E. coli* and *S. aureus* ($p < 0.05/0.01$) for the cure of corneas infection (Xiang et al., 2024). Moreover, other nanoparticles are being widely incorporated in imaging techniques such as magnetic resonance imaging (MRI), fluorescence-labelled imaging, Computed Tomography (CT), and others for more accurate detection and diagnosis of diseases. Studies show that porous and solid gold nanoparticles improved the detection of lung cancer (Ashton, Gottlin, Patz Jr, West, & Badea, 2018). Thus, in diagnostics and imaging, nanoparticles are providing solutions to the current limitations of various techniques by accurate and targeted diagnosis.

6.3 Theranostics

Theranostics is an advance field of medicine combining both diagnostics and treatment therapies. Nanoparticles showed great advancement in theranostics as they provide accurate and targeted diagnosis and treatment options (Y. Wu et al., 2021). Studies show that gold quantum dot nanoparticles inhibit the growth of tumor cells by reducing the metastatic events thus are used in cancer therapy (Wahab et al., 2019). Carbon nanotubes because of their surface area, mechanical strength, thermal and electrical conductivity and stability are used as drug carrier and also as imaging contrast agent (Alshamrani, 2022). Another nanomaterial chitosome(liposome nanoparticles coated with chitosan) loaded with luteolin are used for brain targeted delivery to treat Alzheimer (Abbas et al., 2022). In cancer theranostics, gold nanoparticles manufactures through green nanotechnology showed long term and efficient therapies as they excel the targeted drug delivery and diagnostic imaging (Sakore, Bhattacharya, Belemkar, Prajapati, & Elossaily, 2024). **Mn:ZnS Quantum Dots@Cellulose Nanofibrils (CNFs) Hydrogel Biosensor** detects glutathione (GSH) in blood plasma effieciently with high sensitivity and providing uncontaminated detection (X. Li, Qin, & Hu, 2023).

Although nanoparticles are of great use and provide broad spectrum of biomedical application, but toxicity and biocompatibility of nanoparticles should be considered very carefully.

6.4 Tissue Engineering and regenerative medicine

Tissue engineering and regenerative medicines (TERM) involve the repairing and replacement of damaged cells or tissues. Nanoparticles offer a great help by their unique properties like surface

area, biocompatibility, and antimicrobial properties (Eivazzadeh-Keihan et al., 2020). In TERM one of the most important studies involve extracellular matrix (ECM) as it regulates the cell function (Hussey, Dziki, & Badylak, 2018). Nanoparticles play a key role in TERM as they can mimic the properties of ECM by facilitating the growth of cells. Several strategies are used to mimic the properties of ECM, one of which is multifunctional scaffolds that are designed to support the cell growth and proliferation to form desired tissues (Chen et al., 2022). For example, β -TCP/BG_Cu (β -tricalcium phosphate/bioactive glass coated with copper oxide nanoparticles) proved to be promising as multifunctional scaffold in bone regeneration and exhibit strong antimicrobial activity while maintaining cell viability in bone tissue engineering (Oliveira et al., 2024).

Likewise, Iron Oxide derived nanoparticles are used in the magnetothermal approach in stem cell therapy and tissue engineering for in-vivo tracking, and magnetic targeting of transplanted stem cells specially in mesenchymal stem cells without disrupting proliferation and differentiation (Liu et al., 2022). Further, researchers found potential in hydrogels and gold nanoparticles in cardiac and nerve tissue engineering because of their properties like structural support, and self-healing properties. Besides their applications, it is necessary to evaluate the functionality and optimization of nanoparticles to fully achieve the desired results (Tohidi, Maleki, & Simchi, 2024).

6.5 Biosensors and Diagnostics

A biosensor is an electronic device that helps in identifying the biological component through a transducer by producing the signal and is widely used in diagnostics and therapeutics (Karunakaran & Keskin, 2022). Due to the broad range of applications of the nanoparticles, they are being used in biosensors for diagnostic purposes by increasing sensitivity and specificity. Studies show that biosensors made of micro screen printed electrodes (μ SPE) and modified Au-Pt nanoparticles are used in the detection of glucose level with fast response, higher sensitivity, and wide concentration range from 0.1nM to 500 μ M (Mahobiya et al., 2023). Biosensors with nanoparticles are also being used to increase the precision and reliability of early detection of various diseases. Electrochemical biosensors with an array of modifying carbon nanotubes are developed for the detection of multiple biomarkers like C- reaction protein (CRP), carbohydrate antigen 125 (CA125), carcinoembryonic antigen (CEA) in human serum plasma for cancer detection (Yan et al., 2024). For the early detection of diabetes, scientist used the machine learning (ML) tool, the techniques involved for its early detection with high accuracy are k-nearest neighbor (KNN) and Random Forest algorithm. Experiment shown that k-nearest neighbor (KNN) achieved an accuracy of 98% while Random Forest algorithm shows an accuracy of 87% for early diagnosis of diabetes (Noviyanti & Alamsyah, 2024) (Ullah et al., 2022) Despite their promising applications, there are certain limitations related to nanoparticles like reproducibility, cost issues, and time that are the main concerns of research.

6.6 Biocatalyst

Biocatalysts are biological molecules or enzymes that speed up the rate of chemical reaction by lowering the activation energy and thus increasing the efficiency and specificity. It is often facilitated by enzyme immobilization, a technique used in industrial processes for the stability and further recovery of enzymes (Sharma, Gupta, Princy, Arya, & Kaur, 2022). Magnetic nanoparticles like magnetite Fe_3O_4 are being used in enzyme immobilization due to their strong magnetic properties, low toxicity, and biocompatibility with biological materials (Fortes, Daniel-da-Silva, Xavier, & Tavares, 2017).

Nano-biocatalysts are being used in various fields such as drug delivery, pharmaceutical, waste treatment, biofuel, etc. Nano porous core shell particles like lipid polymer hybrid particles shows potential in drug delivery (Mukherjee et al., 2019). Glucose oxidase enzyme immobilized on selenium nanoparticles are used in biosensors for determination of glucose in body fluids. Literature reports show that cellulases immobilized on gold coated magnetic silica nanoparticles are used in the generation of biofuels (Razzaghi et al., 2022). They also have been used in biomedicine. It is reported that folic acid-functionalized chitosan nanoparticles are used to deliver catalase in case of spinal cord injury because the efficacy of drug was limited in that particular disease (Y. Li et al., 2024).

While using nanomaterial in any application, their toxicity, and biodegradability should be considered for safe and eco-friendly use.




Fig. 3: Nanomaterial Applications in Drug Delivery and Diagnostics (This diagram has been prepared by BioRender <https://BioRender.com>)

7. Stimuli-Responsive Nanomaterials

Stimuli-responsive nanomaterials (SRNs), also termed "Smart Nanomaterials," have significant biomedical applications due to their ability to change physicochemical properties according to stimuli. This is beneficial for drug delivery as it prevents the untimely release of drugs, for diagnosis, wound healing, etc (Table 1). Nevertheless, designing nanoparticles that respond to specific stimuli after entering the complex and dynamic biological system is challenging and needs attention.

Interestingly, SRNs are designed for precise drug delivery and releasing therapeutic drugs upon the onset of specific stimuli. These stimuli are categorized as internal (e.g., pH, redox, enzymatic activity, and ionic strength) and external (e.g., temperature, light, magnetic fields, and ultrasound), some of their examples and biomedical applications are enlisted in Table 2.

Table 1: Stimuli-responsive Nanomaterials and their Biomedical Applications

Stimulus Type	Stimulus	Nanomaterials	Biomedical Applications	References
Internal	pH	PEGylated DOX-MSNs, poly(l-histidine) grafted carbon nanotube	Release drug specific environment targeted	(Mal et al., 2022) , pH for Hashemzadeh, & Farzad, 2022)
	ZIF-8 (Zeolitic Imidazolate Framework-8)		Drug delivery Metal-organic framework use for Drug Delivery and Bioimaging	(Tan, Wu, & Wen, 2021)
	Redox	PEGylated mesoporous silica core-shell redox-responsive nanoparticles	Paclitaxel delivery for breast cancer	(Shahbaz et al., 2024)
	Enzymatic	Hyaluronic Acid-Coated Nanomedicine	Use in Cancer therapy, release drug in the presence of hyaluronidase	(Kim, Choi, Choi, Park, & Ryu, 2019; Yi Li et al., 2024)
External	Ionic Strength	chitosan nanoparticles	Influences aggregation and stability by screening electrostatic interactions	(Sapre, Gumathannavar, Jadhav, Kulkarni, & Shirolkar, 2022)
	Temperature	poly (N-isopropyl acrylamide) nanoparticles	delivery of simvastatin acid in hyperthermic conditions	(Zarrin, Mottaghitalab, Reis,

Kundu, & Farokhi, 2022)

Light	chitosan nanoparticles	drug targeting towards MDA-MB-453 cells	(Karuppaiah et al., 2021)
Magnetic Field	Fe ₃ O ₄ -CA nanoparticles	magnetically active scaffolds Changes in gene expression profile of normal human fibroblasts	(Botvin et al., 2024)
Ultrasound	microbubbles (MBs) coated Cu-Se nanoparticles	anticancer activity in human ovarian cancer cells	(Han, Liu, Wang, & Zhou, 2020)

7.1 RNMs (Responsive Nanomaterials) in Disease Detection and Treatment

7.1.1 Introduction to RNMs

Responsive nanomaterials are being created to developed innovative unique functionalities [11]. Responsive nanomaterials are a flexible and energetic type of materials that have the ability to respond to various stimuli, making them very useful in areas such as medicine, sensing and imaging. These abilities make them efficient and enhanced their functionality.

Table 2: Responsive nanomaterials and their Biomedical Applications

Types	Bio Relevant Stimuli	Applications	Reference
Biologically Responsive Nanomaterials	<ul style="list-style-type: none">• PH• redox potentials	<ul style="list-style-type: none">• Biosensing• bioimaging• photoacoustic imaging	(Jiang, Han, Zhao, Wang, & Tang, 2022)
Optical Responsive Nanomaterials	<ul style="list-style-type: none">• Temperature• pH• ionic strength• humidity	<ul style="list-style-type: none">• Biomedicine sensing• photocatalysis	(Z. Li, He, & Zeng, 2021)
Enzyme-Responsive Nanomaterials	<ul style="list-style-type: none">• Temperature• light• magnetic field• ultrasound• light	<ul style="list-style-type: none">• theranostics	(Mu, Lin, Huang, & Chen, 2018)

ZnO-Based Responsive Nanomaterials	<ul style="list-style-type: none"> • light, • ultrasound • electricity • magnetic field 	<ul style="list-style-type: none"> • anticancer • antimicrobial • biosensors • tooth bleaching 	(Weng, Xu, Gao, & Wang, 2023)
Electrochemically Responsive Nanomaterials	<ul style="list-style-type: none"> • Temperature • pH 	<ul style="list-style-type: none"> • daptive materials • responsive electrochromic • architectures • drug delivery • bioimaging • sensing 	(Hamidinejad, Wang, Sanders, & De Volder, 2024)
Target-Responsive Nanomaterials	<ul style="list-style-type: none"> • Electrochemical and Optical/Colorimetric stimuli 	<ul style="list-style-type: none"> • drug delivery • bioimaging • sensing 	(X. Zhang et al., 2022)
Cellulose-Based Responsive Nanomaterials	<ul style="list-style-type: none"> • Humidity • pH • pressure, • electricity 	<ul style="list-style-type: none"> • Ctuators • sensors • smart coatings • nanogenerators 	(Zhu et al., 2020)
Polymeric Responsive Nanomaterials	<ul style="list-style-type: none"> • Temperature • pH • light • magnetic or electric fields 	<ul style="list-style-type: none"> • drug delivery • sensors • separation membranes • catalysis 	(J. Zhao, Lee, Liu, & Priestley, 2019)
Stimuli-Responsive Nanomaterials	<ul style="list-style-type: none"> • PH • temperature • light • enzyme presence 	<ul style="list-style-type: none"> • Drug delivery 	(Pham, Choi, & Choi, 2020)

8. Challenges and Limitations in Nano medicine

8.1 Toxicity and Biocompatibility Concerns

Nanoparticles are of great interest in biomedical research, improved diagnostics and treatment therapies. However there are several concerns related to nanoparticles especially toxic effect of nanoparticles like silica nanoparticles which are most widely used as drug carrier (Toshalieva et al., 2024). Studies show that SiNPs can induce cytokine response in bronchial cells (BEAS-2B, HBEC3-KT) (Låg et al., 2018) which can lead to chronic inflammation.

Another main concern is the biocompatibility of nanoparticles which includes several factors like accumulation, size, shape, surface chemistry and physicochemical properties (Verma et al., 2021).

Accumulation of metal oxide nanoparticles can lead to oxidative stress induction and apoptosis. As CuO NP was found as anticancer agent (Naz, Gul, Zia, & Javed, 2023) and was widely used, they were studied to check the toxicity and biocompatibility and studies found that they were cytotoxic and can cause increase in reactive oxygen species (ROS) generation (Katsumi et al., 2018).

So considering these limitations there should be careful selection and preparation of nanoparticles in diagnostics and treatment otherwise these nanoparticles can be damaging and even lethal.

8.2 Manufacturing and scalability

Key parameters of nanoparticles that are used in biomedical research are size, shape, morphology, size distribution, targetability and functionality (Patel, Patel, & Patel, 2021). Keeping in mind all these points, there are two main challenges in manufacturing and scalability of nanoparticles that are size and cost. In biomedical research, achieving a consistent size and managing interfacial bonding hindering is a major task. Further challenges involve aggregation, contamination, degradation, and low yield during the production of nanoparticles (Nnamani Akinniyi et al., 2024).

Also large scale production of nanomedicines leads to various challenges and limitations. Studies show that large scale production of nanomedicine from a laboratory batch results in decreased size due to increase in impeller speed and agitation time (Muthu & Wilson, 2012).

Another challenge in the manufacturing of nanoparticles is to produce biosynthesized nanoparticles that are environment friendly and safe to use as cleaner and safer environment has become our top priority (Khan, Karimi, & Khan, 2023).

8.3 Regulatory and Ethical Issues

For the safe and sustainable integration of nanotechnology in the society, regulatory policies are must for safeguarding human health, preserving environment and building public trust (Isibor, 2024). The extensive use of nanoparticles (e.g., AgNPs, AuNPs, ZnONPs) can potentially damage the environment due to their ability to interact with living organisms and wildlife, especially in the absence of regulations or policies governing their use (Tran et al., 2024). So, now nanoparticles and nanomedicine undergo approval process to ensure their safety, efficacy, and quality by regulatory bodies FDA, the European Medicines Agency (EMA), and China's National Medical Products Administration (NMPA). From 2003-2011, the United States took initiative for regulatory measures in nanotechnology like the 2007 EPA Nanotechnology White Paper, 2009 Nanomaterials Research Strategy, and the 2011 Nanotechnology EHS Research Strategy (Ma et al., 2024). Thus, before implementation of any application of nanotechnology regulatory and ethical values should be considered.

9. Future Perspectives and Unexplored Areas in Nanomedicine

Nano medicine is considered an encouraging candidate for upcoming medical studies because of its widespread applications such as antibacterial activities against bacterial infections (Zeng et al., 2024), for efficient immunosuppression retrogression (Y. Zhang et al., 2024), for treatment of post-surgery tumors such as tumor recurrence and lung cancer (K. Zhang et al., 2023). Nanomaterials have gained a significant research interest as the next generation of tissue repair materials, which are developed in tissue engineering and therapeutic regeneration to restore, maintain or enhance the capability of harmed tissues and organs (L. Zhang & Webster, 2009). These progressive steps highlight the therapeutic and diagnostic ability of novel Nano medicines while clearing the path for upcoming clinical deployments.

Advances in Smart and Stimuli-Responsive Nano materials for precision medicine.

The nanoparticles are designed in such a way that they are able to respond to specific triggers. Such as NIR light, PH changes, and reducing agents. Due to these triggers the nanoparticles can release drugs into the cells where the cancer cells are present in the body. When nanoparticles are exposed to NIR light, they heat up and causes photo-induced hyperthermia which can lead to kill cancer cell more effectively (An et al., 2016). In the coming days, investigating novel stimuli and improving stimuli-responsive nanomaterials will not only create novel opportunities in nano medicine but also facilitating more targeted, beneficial and personalized cancer treatments.

Potential for Sustainable and Green Nano materials in reducing environmental impact

By searching for natural reducers and stabilizers, there is an increasing demand for nano materials. It cause reduction in Non-green methods for example chemicals that are toxic for natural systems as well as toxic for human health (Villegas-Fuentes, Castellano, Vilchis-Nestor, & Luque, 2024). For instance, for the formation of TiO₂ nanoparticles the extract of *Annona muricata* L., that possess a significant antioxidant power, has been found to be a Potent reducing agent (Asmat-Campos, Rojas, & Carreño-Ortega, 2023). Similarly, ZnO nanoparticles which are synthesized by *Bauhinia forficata* extract show excellent photocatalytic activity under UV light emphasizing its capability for ecological cleanup and effluent rectification. This methodology can lead to the degradation of many dyes including methylene blue (98.0 %), methyl orange (84.4 %), rhodamine-B (94.64 %), Congo red (95.5 %), and malachite green (98.2 %), respectively (Villegas-Fuentes et al., 2024). Collectively this study tells the importance of green or sustainable nano materials in reducing environmental impact, on the other hand making progress in technologies develop for clean energy, and pollution control.

Emerging applications in Personalized Medicine and real-time health monitoring.

Small size of nanomaterials makes them differ significantly from their Larger-scale materials, it can lead to new opportunities for developing novel therapies, targeted drug delivery systems, and sensitive diagnostic tools. Moreover, with the help of Nanotechnology-based sensors and devices we can assess the medical condition of patient immediately, which allow quick diagnosis and personalized care strategies. Over time nanotechnology may pave the way for creation of nanorobots to remove cancerous growths or to carry the drugs to designated area that can move

through the circulatory system (Malik, Muhammad, & Waheed, 2023). For better individualized care nano based gene therapy provides targeted DNA repair allowing personalized cares and real time health monitoring.

10. Conclusion

Nanotechnology promises to have a great effect on the progress of novel theranostic, diagnostic, imaging, regenerative medicine and therapeutic strategies. A lot of drugs facilitated by nanomaterials had been introduced in the market which showed very positive impact on modern biomedical science. Through focused and systematic release, nanomaterials not only enhance the drug delivery system but also play vital role in early disease detection by using gold nanoparticles through diagnostic, biosensors or bioimaging and also contributed to regenerative medicine and tissue engineering. However, issues such as toxic effect of nanoparticles, biocompatibility, aggregation, contamination, degradation, scalability remain key challenges to their widespread use. Moreover, regulatory and ethical hurdles need to be tackled for the safe and sustainable integration of nanotechnology in the biomedical industry.

References:

Abbas, H., Sayed, N. S. E., Youssef, N. A. H. A., M. E. Gaafar, P., Mousa, M. R., Fayed, A. M., & Elsheikh, M. A. (2022). Novel Luteolin-Loaded Chitosan Decorated Nanoparticles for Brain-Targeting Delivery in a Sporadic Alzheimer's Disease Mouse Model: Focus on Antioxidant, Anti-Inflammatory, and Amyloidogenic Pathways. *Pharmaceutics*, 14(5), 1003.

Albuquerque, L. J. C., Sincari, V., Jäger, A., Kucka, J., Humajova, J., Pankrac, J., . . . Jäger, E. (2021). pH-responsive polymersome-mediated delivery of doxorubicin into tumor sites enhances the therapeutic efficacy and reduces cardiotoxic effects. *Journal of Controlled Release*, 332, 529-538. doi:10.1016/j.jconrel.2021.03.013

Alshamrani, M. (2022). Broad-Spectrum Theranostics and Biomedical Application of Functionalized Nanomaterials. *Polymers*, 14(6), 1221.

An, X., Zhu, A., Luo, H., Ke, H., Chen, H., & Zhao, Y. (2016). Rational design of multi-stimuli-responsive nanoparticles for precise cancer therapy. *ACS Nano*, 10(6), 5947-5958.

Anees, M., Mehrotra, N., Tiwari, S., Kumar, D., Kharbanda, S., & Singh, H. (2023). Polylactic acid based biodegradable hybrid block copolymeric nanoparticle mediated co-delivery of salinomycin and doxorubicin for cancer therapy. *International Journal of Pharmaceutics*, 635, 122779.

Ashton, J. R., Gottlin, E. B., Patz Jr, E. F., West, J. L., & Badea, C. T. (2018). A comparative analysis of EGFR-targeting antibodies for gold nanoparticle CT imaging of lung cancer. *PLoS One*, 13(11), e0206950.

Asmat-Campos, D., Rojas, M. L., & Carreño-Ortega, A. (2023). Toward sustainable nanomaterials: an innovative ecological approach for biogenic synthesis of TiO₂ nanoparticles with potential photocatalytic activity. *Cleaner Engineering and Technology*, 17, 100702.

Baati, T., Chaabani, I., Salek, A., Njim, L., Selmi, M., Al-Kattan, A., & Hosni, K. (2023). Chitosan-coated ultrapure silicon nanoparticles produced by laser ablation: biomedical potential in nano-oncology as a tumor-targeting nanosystem††Electronic supplementary information

(ESI) available. See DOI: <https://doi.org/10.1039/d3na00253e>. *Nanoscale Advances*, 5(11), 3044-3052. doi:<https://doi.org/10.1039/d3na00253e>

Barenholz, Y. C. (2012). Doxil®—The first FDA-approved nano-drug: Lessons learned. *Journal of Controlled Release*, 160(2), 117-134.

Bayda, S., Adeel, M., Tuccinardi, T., Cordani, M., & Rizzolio, F. (2019). The history of nanoscience and nanotechnology: from chemical-physical applications to nanomedicine. *Molecules*, 25(1), 112.

Botvin, V. V., Sukhinina, E. V., Fetisova, A. A., Wagner, D. V., Vedyashkina, M. Y., Pryadko, A., . . . Surmenev, R. A. (2024). Changes in gene expression profile of normal human fibroblasts on P (VDF-TrFE) scaffolds highly doped with Fe₃O₄-CA nanoparticles under alternating magnetic field stimulation. *European Polymer Journal*, 220, 113492.

Chen, Y., Dong, X., Shafiq, M., Myles, G., Radacsi, N., & Mo, X. (2022). Recent Advancements on Three-Dimensional Electrospun Nanofiber Scaffolds for Tissue Engineering. *Advanced Fiber Materials*, 4(5), 959-986. doi:10.1007/s42765-022-00170-7

Damgé, C., Michel, C., Aprahamian, M., & Couvreur, P. (1988). New approach for oral administration of insulin with polyalkylcyanoacrylate nanocapsules as drug carrier. *Diabetes*, 37(2), 246-251.

Darré, T., Tchandikou, L., Simgban, P., Bombone, M., Djiba, T., N'Timon, B., . . . Napo-Koura, G. (2023). Factors associated with late diagnosis of breast cancer in women in Togo, Sub-Saharan Africa. *BMC Women's Health*, 23(1), 106. doi:10.1186/s12905-023-02257-8

Deena Dayal, S., Pushpa Rani, V., Antony Prabhu, D., Rajeshkumar, S., David, D., & Francis, J. (2024). Formulation and evaluation of Phaseolus lunatus seed coat mediated silver nanoparticles mouthwash: A comprehensive study on biomedical properties and toxicological assessment. *Microb Pathog*, 197, 107033. doi:10.1016/j.micpath.2024.107033

Eivazzadeh-Keihan, R., Bahojb Noruzi, E., Khanmohammadi Chenab, K., Jafari, A., Radinekiyan, F., Hashemi, S. M., . . . Hamblin, M. R. (2020). Metal-based nanoparticles for bone tissue engineering. *Journal of Tissue Engineering and Regenerative Medicine*, 14(12), 1687-1714. doi:10.1002/term.3131

El-Sheekh, M. M., Alwaleed, E. A., Kassem, W. M., & Saber, H. (2020). Antialgal and antiproliferative activities of the algal silver nanoparticles against the toxic cyanobacterium *Microcystis aeruginosa* and human tumor colon cell line. *Environmental Nanotechnology, Monitoring & Management*, 14, 100352.

Encabo-Berzosa, M. M., Sancho-Albero, M., Sebastian, V., Irusta, S., Arriuebo, M., Santamaria, J., & Martín Duque, P. (2017). Polymer functionalized gold nanoparticles as nonviral gene delivery reagents. *The journal of gene medicine*, 19(6-7), e2964.

Esmaeili, Y., Khavani, M., Bigham, A., Sanati, A., Bidram, E., Shariati, L., . . . Rafienia, M. (2022). Mesoporous silica@chitosan@gold nanoparticles as "on/off" optical biosensor and pH-sensitive theranostic platform against cancer. *Int J Biol Macromol*, 202, 241-255. doi:10.1016/j.ijbiomac.2022.01.063

Etefa, H. F., Nemera, D. J., Etefa, K. T., & Kumar, E. R. (2024). Evaluation of physicochemical properties of zinc oxide and indium-tin oxide nanoparticles for photocatalysis and biomedical activities. *Current Applied Physics*, 67, 133-142. doi:10.1016/j.cap.2024.08.001

Fan, J., Li, X., Jin, M., & Li, C. (2024). Synthesis and biological evaluation of gold nanoparticles drug delivery system for anti-rheumatoid arthritis agents. *Journal of Drug Delivery Science and Technology*, 102. doi:10.1016/j.jddst.2024.106402

Faraday, M. (1857). X. The Bakerian Lecture.—Experimental relations of gold (and other metals) to light. *Philosophical transactions of the Royal Society of London*(147), 145-181.

Farinha, P., Coelho, J. M. P., Reis, C. P., & Gaspar, M. M. (2021). A Comprehensive Updated Review on Magnetic Nanoparticles in Diagnostics. *Nanomaterials*, 11(12), 3432. doi:10.3390/nano11123432

Feynman, R. (2018). There's plenty of room at the bottom *Feynman and computation* (pp. 63-76): CRC Press.

Fortes, C. C. S., Daniel-da-Silva, A. L., Xavier, A. M. R. B., & Tavares, A. P. M. (2017). Optimization of enzyme immobilization on functionalized magnetic nanoparticles for laccase biocatalytic reactions. *Chemical Engineering and Processing: Process Intensification*, 117, 1-8. doi:10.1016/j.cep.2017.03.009

Freestone, I., Meeks, N., Sax, M., & Higgitt, C. (2007). The Lycurgus cup—a roman nanotechnology. *Gold bulletin*, 40, 270-277.

Haghi, A., Raissi, H., Hashemzadeh, H., & Farzad, F. (2022). Development of the poly (l-histidine) grafted carbon nanotube as a possible smart drug delivery vehicle. *Computers in Biology and Medicine*, 143, 105336.

Hamidinejad, M., Wang, H., Sanders, K. A., & De Volder, M. (2024). Electrochemically Responsive 3D Nanoarchitectures. *Advanced Materials*, 36(2), 2304517.

Han, W., Liu, X., Wang, L., & Zhou, X. (2020). Engineering of lipid microbubbles-coated copper and selenium nanoparticles: Ultrasound-stimulated radiation of anticancer activity in human ovarian cancer cells. *Process Biochemistry*, 98, 113-121.

Hardenberg, G., Brouwer, C., van Gemerden, R., Jones, N. J., Marriott, A. C., & Rip, J. (2024). Polymeric nanoparticle-based mRNA vaccine is protective against influenza virus infection in ferrets. *Molecular Therapy-Nucleic Acids*, 35(1).

Hoyos-Palacio, L. M., Castro, D. P. C., Ortiz-Trujillo, I. C., Palacio, L. E. B., Upegui, B. J. G., Mora, N. J. E., & Cornelio, J. A. C. (2019). Compounds of carbon nanotubes decorated with silver nanoparticles via in-situ by chemical vapor deposition (CVD). *Journal of materials research and technology*, 8(6), 5893-5898.

Hussey, G. S., Dziki, J. L., & Badylak, S. F. (2018). Extracellular matrix-based materials for regenerative medicine. *Nature Reviews Materials*, 3(7), 159-173.

Iqbal, H., Razzaq, A., Zhou, D., Lou, J., Xiao, R., Lin, F., & Liang, Y. (2024). Nanomedicine in glaucoma treatment: Current challenges and future perspectives. *Materials Today Bio*, 28. doi:10.1016/j.mtbiol.2024.101229

Isibor, P. O. (2024). Regulations and Policy Considerations for Nanoparticle Safety. In P. O. Isibor, G. Devi, & A. A. Enuneku (Eds.), *Environmental Nanotoxicology: Combatting the Minute Contaminants* (pp. 295-316). Cham: Springer Nature Switzerland.

Jain, S., Sahu, N., Bhatia, D. D., & Yadav, P. D. (2024). Cellular uptake and viability switch in the properties of lipid-coated carbon quantum dots for potential bioimaging and therapeutics. *bioRxiv*, 2024.2003. 2031.587464.

Jia, Y., Jiang, Y., He, Y., Zhang, W., Zou, J., Magar, K. T., . . . He, W. (2023). Approved Nanomedicine against Diseases. *Pharmaceutics*, 15(3), 774.

Jiang, Z., Han, X., Zhao, C., Wang, S., & Tang, X. (2022). Recent advance in biological responsive nanomaterials for biosensing and molecular imaging application. *International Journal of Molecular Sciences*, 23(3), 1923.

Jin, J. H., Um, H., Oh, J. H., Huh, Y., Jung, Y., & Kim, D. (2022). Gadolinium silicate-coated porous silicon nanoparticles as an MRI contrast agent and drug delivery carrier. *Materials Chemistry and Physics*, 287, 126345. doi:https://doi.org/10.1016/j.matchemphys.2022.126345

John, M. S., Nagoth, J. A., Ramasamy, K. P., Mancini, A., Giuli, G., Natalello, A., . . . Pucciarelli, S. (2020). Synthesis of bioactive silver nanoparticles by a *Pseudomonas* strain associated with the antarctic psychrophilic protozoon *Euplotes focardii*. *Marine drugs*, 18(1), 38.

Karunakaran, R., & Keskin, M. (2022). Biosensors: components, mechanisms, and applications. *Analytical Techniques in Biosciences* (pp. 179-190): Elsevier.

Karuppaiah, A., Babu, D., Selvaraj, D., Natrajan, T., Rajan, R., Gautam, M., . . . Sankar, V. (2021). Building and behavior of a pH-stimuli responsive chitosan nanoparticles loaded with folic acid conjugated gemcitabine silver colloids in MDA-MB-453 metastatic breast cancer cell line and pharmacokinetics in rats. *European Journal of Pharmaceutical Sciences*, 165, 105938.

Kateb, B., & Heiss, J. D. (2013). Nanoneuroscience and Nanoneurosurgery. *The Textbook of Nanoneuroscience and Nanoneurosurgery*, 547-556.

Katsumi, A., Thorley, A. J., Arostegui, I., Reip, P., Valsami-Jones, E., Tetley, T. D., & Cajaraville, M. P. (2018). Cytotoxicity and cellular mechanisms of toxicity of CuO NPs in mussel cells in vitro and comparative sensitivity with human cells. *Toxicol In Vitro*, 48, 146-158. doi:10.1016/j.tiv.2018.01.013

Khan, F., Karimi, M. N., & Khan, O. (2023). Exploring the scalability and commercial viability of biosynthesized nanoparticles for cooling panels with the help of Artificial Intelligence and solar energy systems. *Green Technologies and Sustainability*, 1(3). doi:10.1016/j.grets.2023.100036

Kim, K., Choi, H., Choi, E. S., Park, M.-H., & Ryu, J.-H. (2019). Hyaluronic acid-coated nanomedicine for targeted cancer therapy. *Pharmaceutics*, 11(7), 301.

Kuin, O. S., Van der Mei, H. C., Busscher, H. J., & Neut, D. (2013). Biodegradable vs non-biodegradable antibiotic delivery devices in the treatment of osteomyelitis. *Expert opinion on drug delivery*, 10(3), 341-351.

Kolodin, A., Syrovashin, M., & Korotaev, E. (2024). Gold nanoparticle microemulsion films with tunable surface plasmon resonance signal. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 701, 134904.

Kreuter, J. (2007). Nanoparticles—a historical perspective. *International Journal of Pharmaceutics*, 331(1), 1-10.

Kundu, M., Chatterjee, S., Ghosh, N., Manna, P., Das, J., & Sil, P. C. (2020). Tumor targeted delivery of umbelliferone via a smart mesoporous silica nanoparticles controlled-release drug delivery system for increased anticancer efficiency. *Mater Sci Eng C Mater Biol Appl*, 116, 111239. doi:10.1016/j.msec.2020.111239

Låg, M., Skuland, T., Godymchuk, A., Nguyen, T. H. T., Pham, H. L. T., & Refsnes, M. (2018). Silica Nanoparticle-induced Cytokine Responses in BEAS-2B and HBEC3-KT Cells: Significance of Particle Size and Signalling Pathways in Different Lung Cell Cultures. *Basic & Clinical Pharmacology & Toxicology*, 122(6), 620-632. doi:10.1111/bcpt.12963

Lee, H., Lee, J. S., Moor, K. J., Kim, H.-i., Kim, S.-R., Gim, G., . . . Kim, J.-H. (2021). Hand-ground fullerene-nanodiamond composite for photosensitized water treatment and photodynamic cancer therapy. *Journal of Colloid and Interface Science*, 587, 101-109.

Li, X., Qin, J., & Hu, Y. (2023). Switch-on hydrogel biosensor based on self-assembly Mn-doped ZnS QDs and cellulose nanofibrils for glutathione detection. *Microchemical Journal*, 191, 108763.

Li, Y., Phan, V. G., Pan, Z., Xuan, X., Yang, H. Y., Luu, C. H., . . . Thambi, T. (2024). Integrated and hyaluronic acid-coated mesoporous silica nanoparticles conjugated with cisplatin and chlorin e6 for combined chemo and photodynamic cancer therapy. *European Polymer Journal*, 220, 113426.

Li, Y., Zou, Z., An, J., Liu, X., Wu, Q., Sun, J., . . . Tian, H. (2024). Folic acid-functionalized chitosan nanoparticles with bioenzyme activity for the treatment of spinal cord injury. *Eur J Pharm Sci*, 192, 106667. doi:10.1016/j.ejps.2023.106667

Li, Z., He, L., & Zeng, J. (2021). Recent Advances in Responsive Optical Nanomaterials. *Frontiers in Chemistry*, 9, 760187.

Liu, H., Sun, R., Wang, L., Chen, X., Li, G., Cheng, Y., . . . Fan, H. (2022). Biocompatible Iron Oxide Nanoring-Labeled Mesenchymal Stem Cells: An Innovative Magnetothermal Approach for Cell Tracking and Targeted Stroke Therapy. *ACS Nano*, 16(11), 18806-18821. doi:10.1021/acsnano.2c07581

Ma, X., Tian, Y., Yang, R., Wang, H., Allahou, L. W., Chang, J., . . . Poma, A. (2024). Nanotechnology in healthcare, and its safety and environmental risks. *Journal of Nanobiotechnology*, 22(1). doi:10.1186/s12951-024-02901-x

Mahmoudi Khatir, N., & Khorsand Zak, A. (2024). Antibacterial activity and structural properties of gelatin-based sol-gel synthesized Cu-doped ZnO nanoparticles; promising material for biomedical applications. *Helijon*, 10(17), e37022. doi:10.1016/j.helijon.2024.e37022

Mahobiya, S. K., Balayan, S., Chauhan, N., Rosario, W., Kuchhal, N. K., Islam, S. S., & Jain, U. (2023). Fabricating a rapid and low-cost electrochemical biosensor with imprints of glycated albumin molecules to detect diabetes using bimetallic Au-Pt nanoparticles on μ SPE. *Applied Surface Science Advances*, 16. doi:10.1016/j.apsadv.2023.100425

Mal, A., Prabhuraj, R., Malhotra, R., Valvi, S. K., Ingle, A., Srivastava, R., . . . Bandyopadhyaya, R. (2022). pH-responsive sustained delivery of doxorubicin using aminated and PEGylated mesoporous silica nanoparticles leads to enhanced antitumor efficacy in pre-clinical orthotopic breast cancer model. *Journal of Drug Delivery Science and Technology*, 77, 103800.

Malik, S., Muhammad, K., & Waheed, Y. (2023). Emerging applications of nanotechnology in healthcare and medicine. *Molecules*, 28(18), 6624.

Mohamedsalih, P. M., & Sabir, D. K. (2020). Antimicrobial activity of silver nanoparticles with antibiotics against clinically isolated *Acinetobacter baumannii*. *Passer Journal of Basic and Applied Sciences*, 2(2), 51-56.

Mu, J., Lin, J., Huang, P., & Chen, X. (2018). Development of endogenous enzyme-responsive nanomaterials for theranostics. *Chemical Society Reviews*, 47(15), 5554-5573.

Mukherjee, A., Waters, A. K., Kalyan, P., Achrol, A. S., Kesari, S., & Yenugonda, V. M. (2019). <p>Lipid–polymer hybrid nanoparticles as a next-generation drug delivery platform: state of the art, emerging technologies, and perspectives</p>. *International Journal of Nanomedicine*, Volume 14, 1937-1952. doi:10.2147/ijn.s198353

Muthu, M. S., & Wilson, B. (2012). Challenges Posed by The Scale-Up of Nanomedicines. *Nanomedicine*, 7(3), 307-309. doi:10.2217/nnm.12.3

Najahi-Missaoui, W., Arnold, R. D., & Cummings, B. S. (2020). Safe Nanoparticles: Are We There Yet? *International Journal of Molecular Sciences*, 22(1), 385. doi:10.3390/ijms22010385

Nasrollahi, S., & Alizadeh, N. (2024). Synthesis of functionalized superparamagnetic iron oxide nanoparticles for ibuprofen and naproxen hydrophobic drugs delivery. *Materials Chemistry and Physics*, 326, 129775.

Naz, S., Gul, A., Zia, M., & Javed, R. (2023). Synthesis, biomedical applications, and toxicity of CuO nanoparticles. *Applied Microbiology and Biotechnology*, 107(4), 1039-1061. doi:10.1007/s00253-023-12364-z

Nnamani Akinniyi, J., Abimbola Atanda, S., Damilola, Ahmed, T., Solomon Ayanda, I., Omolola Badmos, F., . . . Queen Adegbola, R. (2024). Perspective Chapter: Nanocomposites – Unlocking the Potentials for Diverse Applications: IntechOpen.

Noviyanti, C. N., & Alamsyah, A. (2024). Early Detection of Diabetes Using Random Forest Algorithm. *Journal of Information System Exploration and Research*, 2(1).

Oliveira, R. L. M. S., Barbosa, L., Pereira, T. C., Dona, L. R. M., Tabuti, T. G., Tada, D. B., . . . Trichês, E. S. (2024). Multifunctional scaffolds of β -tricalcium phosphate/bioactive glass coated with zinc oxide and copper oxide nanoparticles. *Nano Trends*, 8. doi:10.1016/j.nwnano.2024.100059

Ouyang, Y., Zhou, M., Liu, Y., Zhang, L., Zhong, C., Yang, Q., & Liu, M. (2024). Mg-doped ZnO nanoparticle as an effective nanocarrier in delivery of 5-Fluorouracil anti-gastric cancer drug. *Journal of Molecular Structure*, 1314. doi:10.1016/j.molstruc.2024.138706

Palombarini, F., Masciarelli, S., Incocciati, A., Liccardo, F., Di Fabio, E., Iazzetti, A., . . . Bonamore, A. (2021). Self-assembling ferritin-dendrimer nanoparticles for targeted delivery of nucleic acids to myeloid leukemia cells. *Journal of Nanobiotechnology*, 19(1), 172.

Patel, D. M., Patel, N. N., & Patel, J. K. (2021). Nanomedicine Scale-Up Technologies: Feasibilities and Challenges. In J. K. Patel & Y. V. Pathak (Eds.), *Emerging Technologies for Nanoparticle Manufacturing* (pp. 511-539). Cham: Springer International Publishing.

Pham, S. H., Choi, Y., & Choi, J. (2020). Stimuli-responsive nanomaterials for application in antitumor therapy and drug delivery. *Pharmaceutics*, 12(7), 630.

Razzaghi, M., Homaei, A., Vianello, F., Azad, T., Sharma, T., Nadda, A. K., . . . Iqbal, H. M. N. (2022). Industrial applications of immobilized nano-biocatalysts. *Bioprocess and Biosystems Engineering*, 45(2), 237-256. doi:10.1007/s00449-021-02647-y

Saberi Riseh, R., & Gholizadeh Vazvani, M. (2024). Green synthesis of metal nanoparticles using plant growth promoting rhizobacteria and application in agriculture. *Plant Nano Biology*, 10. doi:10.1016/j.plana.2024.100111

Saji, V. S. (2022). Supramolecular organic nanotubes for drug delivery. *Materials Today Advances*, 14, 100239.

Sakore, P., Bhattacharya, S., Belemkar, S., Prajapati, B. G., & Elossaily, G. M. (2024). The theranostic potential of green nanotechnology-enabled gold nanoparticles in cancer: A paradigm shift on diagnosis and treatment approaches. *Results in Chemistry*, 7. doi:10.1016/j.rechem.2023.101264

Sapre, N., Gumathannavar, R., Jadhav, Y., Kulkarni, A., & Shirodkar, M. M. (2022). Effect of ionic strength on porosity and surface charge of chitosan nanoparticles. *Materials Today: Proceedings*.

Shahali, H., Hasan, J., Wang, H., Tesfamichael, T., Yan, C., & Yarlagadda, P. K. (2019). Evaluation of particle beam lithography for fabrication of metallic nano-structures. *Procedia Manufacturing*, 30, 261-267.

Shahbaz, S., Esmaeili, M., Nasab, M. H. F., Imani, Z., Bafkary, R., Amini, M., . . . Dinarvand, R. (2024). PEGylated mesoporous silica core-shell redox-responsive nanoparticles for delivering paclitaxel to breast cancer cells. *International Journal of Pharmaceutics*, 655, 124024.

Sharma, S., Gupta, S., Princy, Arya, S. K., & Kaur, A. (2022). Enzyme immobilization: Implementation of nanoparticles and an insight into polystyrene as the contemporary immobilization matrix. *Process Biochemistry*, 120, 22-34. doi:10.1016/j.procbio.2022.05.022

Ta, H. K. T., Mai, N. X. D., Nguyen, H.-V. T., Matsumoto, K., Phan, T. B., Tamanoi, F., & Doan, T. L. H. (2024). Development and characterization of magnetic-based biodegradable periodic mesoporous organosilica nanoparticles for enhanced biomedical applications. *Journal of Industrial and Engineering Chemistry*. doi:10.1016/j.jiec.2024.07.061

Tan, C., Wu, J., & Wen, Z. (2021). Doxorubicin-loaded MnO₂@ Zeolitic imidazolate framework-8 nanoparticles as a chemophotothermal system for lung cancer therapy. *ACS omega*, 6(20), 12977-12983.

Tohidi, H., Maleki, N., & Simchi, A. (2024). Conductive, injectable, and self-healing collagen-hyaluronic acid hydrogels loaded with bacterial cellulose and gold nanoparticles for heart tissue engineering. *Int J Biol Macromol*, 280(Pt 2), 135749. doi:10.1016/j.ijbiomac.2024.135749

Tong, W., Hui, H., Shang, W., Zhang, Y., Tian, F., Ma, Q., . . . Chen, Y. (2021). Highly sensitive magnetic particle imaging of vulnerable atherosclerotic plaque with active myeloperoxidase-targeted nanoparticles. *Theranostics*, 11(2), 506-521. doi:10.7150/thno.49812

Toshalieva, S., Hussein, U. A.-R., Nabee, A., Mohammed, F., Mohammed, R., Ali Ahmed, B., . . . Barro Uktamovna, B. (2024). Pulmonary Effects of Silica Nanoparticles in Rats Following Subchronic Inhalation Exposure. *Journal of Nanostructures*, 14(1), 65-72. doi:10.22052/jns.2024.01.006

Tran, T. K., Nguyen, M. K., Lin, C., Hoang, T. D., Nguyen, T. C., Lone, A. M., . . . Nguyen, D. D. (2024). Review on fate, transport, toxicity and health risk of nanoparticles in natural ecosystems: Emerging challenges in the modern age and solutions toward a sustainable environment. *Sci Total Environ*, 912, 169331. doi:10.1016/j.scitotenv.2023.169331

Ullah, Z., Saleem, F., Jamjoom, M., Fakieh, B., Kateb, F., Ali, A. M., & Shah, B. (2022). Detecting High-Risk Factors and Early Diagnosis of Diabetes Using Machine Learning Methods. *Computational Intelligence and Neuroscience*, 2022(1), 2557795.

Usha, P., Prasad, K. H., & Ramesh, S. (2023). NiFe₂O₄ nanoparticles prepared using the sol-gel process: Structural and impedance investigations. *Materials Today: Proceedings*, 92, 1295-1298.

Van, H. N., Nguyen, L. H. T., Mai, N. X. D., Nhat, A. H., Thu, T. L. T., Bao, A. N. T., . . . Doan, T. L. H. (2024). Enhancing Docetaxel Efficacy and Reducing Toxicity Using Biodegradable Periodic Mesoporous Organosilica Nanoparticles. *Heliyon*.

Verma, S. K., Panda, P. K., Kumari, P., Patel, P., Arunima, A., Jha, E., . . . Suar, M. (2021). Determining factors for the nano-biocompatibility of cobalt oxide nanoparticles: proximal discrepancy in intrinsic atomic interactions at differential vicinage. *Green Chemistry*, 23(9), 3439-3458. doi:10.1039/D1GC00571E

Villegas-Fuentes, A., Castellano, L. E., Vilchis-Nestor, A. R., & Luque, P. A. (2024). Sustainable and environmentally friendly synthesis of ZnO semiconductor nanoparticles from Bauhinia forficata leaves extract and the study of their photocatalytic and antibacterial activity. *Cleaner Materials*, 13, 100268.

Wahab, R., Kaushik, N., Khan, F., Kaushik, N. K., Lee, S.-J., Choi, E. H., & Al-Khedhairy, A. A. (2019). Gold quantum dots impair the tumorigenic potential of glioma stem-like cells via β -catenin downregulation in vitro. *International Journal of Nanomedicine*, 1131-1148.

Wang, Y., Zhao, X., Zhou, X., Dai, J., Hu, X., Piao, Y., . . . Liu, Y. (2024). A supramolecular hydrogel dressing with antibacterial, immunoregulation, and pro-regeneration ability for biofilm-associated wound healing. *Journal of Controlled Release*, 368, 740-755.

Weissig, V., Pettinger, T. K., & Murdock, N. (2014). Nanopharmaceuticals (part 1): products on the market. *International Journal of Nanomedicine*, 4357-4373.

Weng, Z., Xu, Y., Gao, J., & Wang, X. (2023). Research progress of stimuli-responsive ZnO-based nanomaterials in biomedical applications. *Biomaterials Science*, 11(1), 76-95.

Wu, H., Tang, L., Dong, H., Zhi, M., Guo, L., Hong, X., . . . Zeng, X. (2024). Shape and Size Dependence of Pharmacokinetics, Biodistribution, and Toxicity of Gold Nanoparticles. *Molecular Pharmaceutics*. doi:10.1021/acs.molpharmaceut.4c00832

Wu, Y., Vazquez-Prada, K. X., Liu, Y., Whittaker, A. K., Zhang, R., & Ta, H. T. (2021). Recent Advances in the Development of Theranostic Nanoparticles for Cardiovascular Diseases. *Nanotheranostics*, 5(4), 499-514. doi:10.7150/ntno.62730

Xiang, J., Zou, R., Wang, P., Wang, X., He, X., Liu, F., . . . Wu, A. (2024). Nitroreductase-responsive nanoparticles for in situ fluorescence imaging and synergistic antibacterial therapy of bacterial keratitis. *Biomaterials*, 308, 122565.

Yan, Y., Liu, Z., Pang, W., Huang, S., Deng, M., Yao, J., . . . Shui, L. (2024). Integrated biosensor array for multiplex biomarkers cancer diagnosis via in-situ self-assembly carbon nanotubes with an ordered inverse-opal structure. *Biosens Bioelectron*, 262, 116528. doi:10.1016/j.bios.2024.116528

Yang, X., Zhou, S., Zeng, J., Zhang, S., Li, M., Yue, F., . . . Luo, J. (2024). A biodegradable lipid nanoparticle delivers a Cas9 ribonucleoprotein for efficient and safe in situ genome editing in melanoma. *Acta Biomaterialia*.

Zarrin, N. K., Mottaghitalab, F., Reis, R. L., Kundu, S. C., & Farokhi, M. (2022). Thermosensitive chitosan/poly (N-isopropyl acrylamide) nanoparticles embedded in aniline pentamer/silk fibroin/polyacrylamide as an electroactive injectable hydrogel for healing critical-sized calvarial bone defect in aging rat model. *International Journal of Biological Macromolecules*, 213, 352-368.

Zeng, W., Liu, J., He, H., Wu, Q., Zhang, Y., Guo, N., & Wang, H. (2024). Carrier-free nanomedicine for combined antibacterial therapy through pH-responsive controlled release of sulfadiazine and emodin. *Journal of Drug Delivery Science and Technology*, 102, 106381.

Zhang, K., Long, Y., Ma, Z., Li, S., Zhao, Y., & Han, H. (2023). Artificial nanoplatelet regulation of tumor immune microenvironment to inhibit post-surgical tumor recurrence and lung metastasis. *Materials Today*, 67, 68-83.

Zhang, L., & Webster, T. J. (2009). Nanotechnology and nanomaterials: promises for improved tissue regeneration. *Nano today*, 4(1), 66-80.

Zhang, X., Zhi, H., Wang, F., Zhu, M., Meng, H., Wan, P., & Feng, L. (2022). Target-responsive smart nanomaterials via a Au-S binding encapsulation strategy for electrochemical/colorimetric dual-mode paper-based analytical devices. *Analytical Chemistry*, 94(5), 2569-2577.

Zhang, Y., Xiang, S., Wu, Y., Yang, C., Tang, D., Chen, Z., & Huang, Z. (2024). Novel co-delivery nanomedicine for photodynamic enlarged immunotherapy by cascade immune activation and efficient Immunosuppression reversion. *Bioorganic Chemistry*, 107978.

Zhao, J., Lee, V. E., Liu, R., & Priestley, R. D. (2019). Responsive polymers as smart nanomaterials enable diverse applications. *Annual Review of Chemical and Biomolecular Engineering*, 10(1), 361-382.

Zhao, Q., Wang, Y., Zhang, M., Wu, D., Sun, J., & Yang, X. (2022). A fluorescence turn-on biosensor utilizing silicon-containing nanoparticles: Ultra-sensitive sensing for α -glucosidase activity and screening for its potential inhibitors. *Biosensors and Bioelectronics*, 214, 114504. doi:<https://doi.org/10.1016/j.bios.2022.114504>

Zhu, Q., Liu, S., Sun, J., Liu, J., Kirubaharan, C. J., Chen, H., . . . Wang, Q. (2020). Stimuli-responsive cellulose nanomaterials for smart applications. *Carbohydrate polymers*, 235, 115933.